



Samur Halilari Sanayi ve Ticaret as Balikhisar M. Koca Seyit Onbasi Caddesi No:13 06750 AKYURT - ANKARA Turkey

**Your notice of** 10-01-2024

Your reference

**Date** 05-02-2024

### Analysis Report 24.00162.01

Required tests:

EN 13501-1 (2019)

Sample id	Information given by the client	Date of receipt
T2400827	Halley Solution Dyed PA carpet tile	10-01-2024

Kristina De Temmerman Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.







Reference: T2400827 - Halley Solution Dyed PA carpet tile

#### Information given by the client

Product standard EN 13501-1 (2019)

Production batch/piece number OI-A

Date of carpet finishing 30-11-2023

FR treated yes
FR-surface treatment no
Type of manufacture Tufted
Use-surface PA

Substrate, support Fibre fleece

Backing layer
Total mass
3750 g/m²
Pile thickness
3.0 mm
Total thickness
5.5 mm
Surface structure
Loop pile

**Notified body No: 0493** 



**Reference:** T2400827 - Halley Solution Dyed PA carpet tile

## <u>Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame - Single-flame source test</u>

Product standard

EN 13501-1 (2019)

Classification of textile floor coverings in accordance with EN 14041 (2004) § 4.1.4

"The textile floor coverings listed in Table 2, in the end uses identified in the table, are classified without further testing (CWFT) in the classes shown and do not require testing in respect of these end uses and classes".

Table 2 – Classes of reaction to fire for textile floor coverings, classified without further testing

Floor covering type <sup>1</sup>	EN product standard	Class <sup>3</sup> Floorings
Non-FR machine-made wall-to-wall carpets and pile carpet tiles <sup>2</sup>	EN 1307	$\mathrm{E}_{\mathrm{fl}}$
Non-FR needled textile floor coverings without pile <sup>2</sup>	EN 1470	$\mathrm{E}_{\mathrm{fl}}$
Non-FR needled textile floor coverings with pile <sup>2</sup>	EN 13297	$\mathrm{E}_{\mathrm{fl}}$

<sup>1)</sup> Floor covering glued or loose laid over a Class A2-s1,d0 substrate

- a surface of 100% wool
- a surface of 80% wool or more 20% polyamide or less
- a surface of 80% wool or more 20% polyamide/polyester or less
- a surface of 100% polyamide
- a surface of 100% polypropylene and if with SBR-foam backing, a total mass of > 0.780 kg/m². All polypropylene carpets with other foam backings are excluded.
- 3) Class as provided for in Table 2 in the Annex to Decision 2000/147/EC.

Textile floor coverings having a total mass of max. 4.8 kg/m², a minimum pile thickness of 1,8 mm (ISO 1766) and





Reference: T2400827 - Halley Solution Dyed PA carpet tile

# <u>Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source</u>

Date of ending the test 02-02-2024

Standard used EN ISO 9239-1 (2010) Product standard EN 13501-1 (2019)

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

#### **Test specimen**

Substrate Fibre cement board - density  $(1800 \pm 200) \text{ kg/m}^3$ 

Mounting Stuck down with

UZIN UZ 57 / Unipro - low emission, solvent-free dispersion adhesive – "EC1 very low emission"

Specimens have not been cleaned

Joint At 25 cm and 75 cm





#### Radiant heat flux

	Flame spread distance (cm)			Flame time	Heat flux *
	10 min	20 min	30 min		kW/m <sup>2</sup>
Width					
#1	14	24	25	26 min 56 s	8.5
Length					
#1	14	24	25	25 min 34 s	8.5
#2	15	24	25	23 min 55 s	8.5
#3	14	24	24	22 min 38 s	8.7
Average					8.6

<sup>\*</sup> Heat flux at the time of flame extinguishment or after a test duration of 30 minutes.

Fire classification in accordance with EN 13501-1 (2019)		
Class	EN ISO 11925-2 or CWFT	EN ISO 9239-1 (test duration = 30 min)
$ m B_{fl}$	$\mathrm{E}_{\mathrm{fl}}$	heat flux $\geq 8.0 \text{ kW/m}^2$
$\mathrm{C}_{\mathrm{fl}}$	$\mathrm{E}_{\mathrm{fl}}$	heat flux $\geq 4.5 \text{ kW/m}^2$
$\mathrm{D}_{\mathrm{fl}}$	$\mathrm{E}_{\mathrm{fl}}$	heat flux $\geq 3.0 \text{ kW/m}^2$

Smoke production: Light attenuation

•	Maximum (%)	Total (%.min)
Width		
#1	7	46
Length		
#1	5	42
#2	7	44
#3	5	40
Average		42

Additional classification in accordance with EN 13501-1 (2019)	
smoke production ≤ 750%.min	s1
smoke production > 750%.min	s2





### Reaction to fire classification : $B_{\rm fl}/s1$

Glued on a non-combustible substrate\*

\* End use substrates of classes A1 or A2-s1,d0 (EN 13238:2010 § 5.2.2)

#### Limitations

This classification document does not represent type approval or certification of the product.